

HYDROSEAL

POLYURETHANE MASTIC SEALANT



USAGE

One-component moisture curing polyurethane sealant in the form of thixotropic paste. After application, in contact with air, the sealant is vulcanised to an elastic and cohesive mass. It is recommended for the sealing and bonding between similar and dissimilar substrates in traditional masonry, civil and industrial applications, light and heavy prefabrications, interior decorating etc. Adheres on most substrates: concrete, glass, wood, anodised aluminium, tiles etc. **HYDROSEAL** is available in white and gray colour. Also, it is paintable.

APPLICATION

Joint preparation: The joint faces to be bonded must be clean, dry and free from dust, oil, grease, old sealant and any traces of contaminant, which may affect adhesion. Surfaces should be degreased with solvent using a clean cloth. To remove dust, use oil-free compressed air.

Priming: **HYDROSEAL** sealant does not normally require primer on most common substrates used in buildings. In cases of expansion joints with porous substrates (concrete), **PRIMER** is recommended. The sealant is applied 15min to 3hrs after the application of the primer.

Joint dimensions: The movement capability of sealant as well as local regulations must be considered. Joint width should be twice the depth when the width is bigger than 20mm and equal to the depth when the width is smaller than 20mm. The width of the joints should not be less than 5 and bigger than 40mm.

Sealant application:

- 1) We cut the nozzle slantwise to form an opening proportional to the joint width.
- 2) We put cartridge/sausage into the hand- or air gun and we apply the sealant in the joint.
- 3) We smooth the surface of the uncured sealant with a spatula, so as to form a slightly negative crescent.

For good performance, it is essential that the sealant be only bonded to the two facing sides of the joint. To achieve this, install a backup material (closed cell polyethylene or open cell polyurethane foam). Apply the sealant in a continuous operation making sure all air pockets or voids are eliminated. Tool the sealant with light pressure to spread the material against the joint surfaces.

This operation should be made with a dry spatula before skin formation occurs.

Excess uncured sealant should be wiped and cleaned with a commercial solvent such as xylene or white spirit; cured sealant can only be removed by abrasion.

PACKAGING

In paper carton with 25 aluminium cartridges of 300 ml or 15 aluminium sausages of 0,6 Lt.

STORAGE

Do not storage the product under high temperatures (>40°C) or under the sun exposition. You can use the product for at least 12 months when stored in original packaging and places with normal temperature and humidity.

SAFETY

The material is classified as dangerous. Keep away from sparks and flames. Do not smoke. Do not inhale, avoid contact with eyes and mouth. Do not apply in closed spaces without adequate air supply. Do not pour it on the ground or water. Always follow the related rules. For additional info ask the MSDS of this material from the producer.

HYDROSEAL

POLYURETHANE MASTIC SEALANT



TECHNICAL SPECIFICATION

Description	Polyurethane Mastic Sealant
Colour	White - Grey
Application Temperature	+5°C to +40°C
Service Temperature	-40°C to +90°C
Properties of Unvulcanized Rubber	
Skin forming time (23 °C, 50% RH)	120-240 min
Curing speed (23 °C, 50% RH)	2-3mm/24h
Density	1,23g/ml
Properties of Vulcanized Rubber	
Hardness (Shore A)	25±5
Movement Capability	25%
Tensile strength (ISO 8339)	0,82 N/mm ²
Modulus at 100% elongation (ISO 8339)	0,32 N/mm ²
Elongation at break (ISO 8339)	550%

ATHENS
Head Office
 111, Lefkias str., Korymbi Attica
 14568, Athens, Greece
 Tel.: +30 210 81.61.857

SALONICA Offices & Distribution Center
 4, Ipeiros str., Kalochori
 57009, Salonica, Greece
 Tel.: +30 2310 79.66.53

INOFYTA
Distribution Center
 55th km National Road Athens/Lamia
 32011, Inofyta, Viotia
 Tel.: +30 22620 30887

CRETA
Offices & Distribution Center
 5th km National Road Iraklio-Moires
 71500, Iraklio, Creta Island
 Tel.: +30 2810 54.32.10

N.ARTAKIEVIA
RoofTile Plant
 Profitis Ilias
 34800, N.Artaki Evia
 Tel.: +30 22210 43985

ARMA VOIOTIAS
Bitumen Products Plant
 Stathmos
 32200, Arma Voiotias
 Tel.: (+30) 22620 72083