

Technical data sheet

XENERGY™ GRP

Thermal resistance R _D	Thickness(mm)	30	40	50	60	70	80	100			
	R _d m ² .K/W	1.00	1.35	1.65	1.95	2.25	2.60	3.20			
Properties	Value	Unit		Standard	CE Code						
Thermal Conductivity Declared (λ _D)	0.030 0.031	< 60 mm ≥ 60 mm		W/m.K	EN 13164	λ _D					
Compressive stress or compressive strength@ 10% deformation	200			kPa	EN 826	CS(10Y)					
Modulus (typical values)	-			MPa	EN 826						
	-			MPa	EN 826						
	-			MPa	EN 826						
Compressive Creep max after 50 years < 2% deformation under stress σ _C	-			kPa	EN 1606	CC(2/1.5/50)σ					
	-			kPa		CC(2/1.5/50)σ					
Tensile strength	-			kPa	EN 1607	TR					
Water vapour diffusion resistance factor μ (tabulated value)	150			-	EN 12086	MU					
Long term water absorption by total immersion	-			%	EN 12087	WL(T)					
Water pick-up by diffusion	-			%	EN 12088	WD(V)					
	-			%		WD(V)					
	-			%		WD(V)					
Water pick up after Freeze Thaw	-			%	EN 12091	FTCD					
Dimensional stability under specified temperature (70°C) and humidity conditions (90%rh)	< 5			%	EN 1604	DS(70,90)					
Dimensional stability under specified compressive load (40kPa) and temperature (70°C) conditions	-				EN 1605	DLT(2)5					
Coefficient of linear thermal expansion (typical value)	0.07			mm/(m.K)	-	-					
Fire performance	E			Euroclass	EN 13501-1						
Temperature limits	-50/+75			°C	-						
Tolerances	Thickness	-1.5/+1.5		mm	EN 823	T2					
	Width	-3/+3		mm	EN 822						
	Length	-10/+10		mm	EN 822						
Dimensions	Thickness	30 - 100		mm	EN 823						
	Width	600		mm	EN 822						
	Length	2500		mm	EN 822						
Edge profile	Ship Lap on the long sides and Butt Edge on the short sides										
Surface finish	Planned with grooves										
CODE CE:	XPS - EN 13164 - T2 - CS(10Y)200 - DS(70,90)										



Note: The information and data contained in this technical data sheet do not represent exact sales specifications. The features of the products mentioned may vary. The information contained in this document has been provided in good faith, however it does not imply any liability, guarantee or assurance of product performance. It is the purchaser's responsibility to determine whether these products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation. No license is hereby granted for the use of patents or other industrial or intellectual property rights. If products are purchased, we advise following the most up-to-date suggestions and recommendations.